



# TECHNICAL DATA SHEET

**JOHN C. DOLPH COMPANY**

P.O. Box 267  
320 New Road  
Monmouth Junction, NJ  
08852

Ph:(732) 329-2333  
Fax:(732) 329-1143  
info@dolphs.com  
www.dolphs.com

## **SYNTHITE® AC-41**

### **CLEAR AIR DRYING VARNISH**

#### **PRODUCT DESCRIPTION**

AC-41 is a high temperature; fast cure, air dry, polyurethane varnish, and is an excellent conformal coating for all electrical and electronic parts. It is especially recommended as a circuit board coating. SYNTHITE® AC-41 is also available in aerosol as **DOLPH - SPRAY® AC-41**.

#### **FEATURES & BENEFITS**

- |   |   |
|---|---|
| <ul style="list-style-type: none"> <li>• Fast drying - Units can be handled in 30 minutes</li> <li>• Ease of Application (dip, brush or spray)</li> <li>• High temperature rating</li> <li>• Excellent chemical resistance</li> </ul> | <ul style="list-style-type: none"> <li>• Oil and moisture resistant</li> <li>• Superior abrasion resistance</li> <li>• Excellent adhesion</li> <li>• UL recognized systems</li> </ul> |
|---|---|

#### **TYPICAL APPLICATIONS**

- |  |   |   |
|--|---|---|
| <ul style="list-style-type: none"> <li>• Field Coils</li> <li>• Control Coils</li> <li>• Motor Frames</li> <li>• Switch Bases</li> <li>• Molded Bakelite</li> <li>• Electrical Connectors</li> </ul> | <ul style="list-style-type: none"> <li>• Collector Rings</li> <li>• Fuse Tubes</li> <li>• Solenoid Coils</li> <li>• Controller Shafts</li> <li>• Printed Circuit Boards</li> <li>• Commutator Ends</li> </ul> | <ul style="list-style-type: none"> <li>• Porcelain</li> <li>• Soldered Joints</li> <li>• Finger Blocks</li> <li>• Oil reservoir interior</li> <li>• Buss bars</li> <li>• Touch up overcoat</li> </ul> |
|--|---|---|

#### **TYPICAL PROPERTIES**

##### **Physical**

<b>Color /Appearance</b>	<b>Clear/Amber</b>
<b>Density @ 77°F (25°C), Lbs/gal</b>	<b>7.0 – 8.0</b>
<b>Viscosity @ 77°F (25°C) Brookfield Viscometer cps</b>	<b>125 – 275</b>
<b>Flash point</b>	<b>81°F (27°C)</b>
<b>Cure Time @ 77°F (25°C) on Strip, min</b>	<b>Set to Touch Tack Free</b> <b>10 30</b>
<b>Film Build, mils/side, ASTM D-115</b>	<b>1-1.5</b>
<b>Thinner (Solvent)</b>	<b>T-200X</b>
<b>Federal Specification, TT-P-1436, Free of After-Tack</b>	<b>1 Hour</b>
<b>VOC-bulk, lb/gal</b>	<b>4.3</b>
<b>VOC-aerosol (calculated)</b>	<b>47%</b>

All statements, technical information and recommendations related to Sellers' products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before using the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liabilities whatsoever in connection with such use. The statements contained herein are made in lieu of all warranties, expressed or implied. Seller shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or inability to use its products. The sole liability of John C. Dolph Co., Inc. for any claims arising out of the manufacture, use or sale of its products shall be for the buyer's purchase price.

**Electrical**

Dielectric Strength, ASTM D 115, \ volts/mil	Dry	2,000
	Wet	1,200

**Chemical Resistance**

Water	Excellent
Acid (10% Sulfuric Acid)	Excellent
Alkali (1% Sodium Hydroxide)	Excellent
Salt Water	Excellent
Oil, ASTM D-115	Passed
Corrosive Effect on Copper	None

**Thermal Class (UL-1446)**

Twisted Pair	MW - 28	130
--------------	---------	-----

**APPLICATION GUIDELINES**

AC-41 may be applied by brush, dip or spray. It is used as supplied in many applications or may be thinned as required with T-200X. For spraying applications, it is usual to thin 20 - 25%.

The film thickness should be kept to no more than 1.5 mils per side per application. This allows for complete solvent release and proper cure. AC-41 will air dry so that it can be handled in 30 minutes. For optimum chemical and abrasion resistance, allow to air dry for at least 24 hours.

**SPECIAL SAFETY PRECAUTIONS**

When AC-41 is applied by spray methods, care should be taken to keep the spray area clean. Filters and other waste from the area should be soaked in water and disposed of in safety containers.

**STORAGE AND SHELF LIFE**

Shelf life (bulk) is one year from date of shipment from our plant, when stored in closed containers at 70°F or below. Shelf Life (Spray) - 18 months @ 70°F (21°C) or cooler.

1. Store in cool, dry place at 70°F/21°C or below.
2. Protect from direct sunlight and sources of heat
3. Keep away from heat, sparks and open flame.

**SAFETY AND ENVIRONMENT**

Avoid contact with skin and eyes. See Material Safety Data Sheet

AUTHORIZED DISTRIBUTOR